

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
25 March 2004 (25.03.2004)

PCT

(10) International Publication Number
WO 2004/024114 A2

(51) International Patent Classification⁷: **A61K 7/46, 7/06**

07039 (US). **LUPO, Andrew, T., Jr.** [US/US]; 8 Powell Road, Emerson, NJ 07630 (US). **SANSONE, Robert, P.** [US/US]; 8 Temple Drive, P.O. Box 296, Tuxedo Park, NY 10987 (US).

(21) International Application Number:
PCT/US2003/028182

(22) International Filing Date:
10 September 2003 (10.09.2003)

(74) Agents: **BERNSTEIN, Mitchell** et al.; Darby & Darby P.C., Post Office Box 5257, New York, NY 10150-5257 (US).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/409,393 10 September 2002 (10.09.2002) US

(81) Designated States (*national*): AF, AG, AI, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(71) Applicants (*for all designated States except US*): **TAKASAGO INTERNATIONAL CORPORATION** [JP/JP]; Nissay Aroma Square, 17F, 37-1, Kamata 5-chome, Ohta-ku, Tokyo 144-8721 (JP). **DOW CORNING S.A.** [BE/BE]; Parc Industriel-zone C, Rue Jules Bordet, B-7180 Seneffe (BE).

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **GIRBOUX, Anne-Lise** [BE/BE]; Avenue Beatrice de Cusance 44, Bte 3, B-1420 Braine l'Alleud (BE). **MARTEAUX, Leon** [BE/BE]; Clos du Bergoje 35, B-1160 Brussels (BE). **NEWTON, Joanne** [GB/BE]; Avenue Steyaert 36, B-1332 Geneval (BE). **POLSTER-RENARD, Catherine** [BE/BE]; Rue de la Prairie 55, B-7830 Hellebecq (BE). **REETH, Isabelle Van** [BE/BE]; 8 Rue Ecole des Filles, B-1315 Incourt (BE). **BARCKLEY, Kathleen A.** [US/US]; 33 Sycamore Avenue, Livingston, NJ

Published:

— *without international search report and to be republished upon receipt of that report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COMPOSITIONS COMPRISING SILICONE-IN-WATER EMULSIONS AND FRAGRANCES AND HAIR CARE PREPARATIONS COMPRISING SUCH COMPOSITIONS

(57) Abstract: The present invention relates to compositions comprising silicone-in-water emulsions and fragrance compositions. It also relates to hair care preparations comprising such compositions, which provide improved release of fragrance when applied to the hair and improved deposition of the fragrance on the hair. The invention is further related to methods of cleansing hair, which comprises applying a hair care preparation to the hair.

WO 2004/024114 A2

Docket No.: 09639/200M018-WO0

5 **COMPOSITIONS COMPRISING SILICONE-IN-WATER EMULSIONS AND**
 FRAGRANCES AND HAIR CARE PREPARATIONS COMPRISING SUCH
 COMPOSITIONS

 The present application is based on U.S. provisional application
10 60/409,393, filed September 10, 2002, which is hereby incorporated herein by
reference in its entirety.

FIELD OF THE INVENTION

 The present invention relates to compositions comprising silicone-in-
15 water emulsions and fragrance compositions. It also relates to hair care preparations
comprising such compositions, which provide improved release of fragrance when
applied to the hair and improved deposition of the fragrance on the hair. The invention
is further related to methods of cleansing hair, which comprises applying a hair care
preparation to the hair.

20

BACKGROUND OF THE INVENTION

 Silicone-in-water emulsions are well known for use in cosmetic
preparations. Hair care preparations with silicone-in-water emulsions have been
described, for example, in WO200203936, EP1093809, and WO200139735. Silicone
25 is lubricious and acts to enhance the properties of the hair by improving the feel, the
shine, and the ease of combing the hair. These compositions may also include
fragrances, which are intended to be released during the application of the composition
and, preferably, be deposited onto the hair for subsequent release. There is, however,
still a need for hair care preparations that can provide improved deposition of
30 fragrances or at least a deposition that will result in a longer lasting release of fragrance
from the hair, without losing the favorable sensory and aesthetic performance qualities
of the product.

It has now surprisingly been found that if an emulsion of a silicone polymer of certain minimum viscosity is introduced in combination with certain fragrances in the cosmetic preparation, better deposition of the fragrance can be achieved without any loss of the essential properties of hair care preparations. The better deposition particularly occurs upon joint introduction of the silicone polymer and the fragrance composition in a single emulsion composition.

SUMMARY OF THE INVENTION

In a first aspect of the invention, there is provided a composition comprising i) a fragrance composition; and ii) a silicone-in-water emulsion comprising at least one surfactant, wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of less than 2 μm . There is further provided a composition comprising: i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 15% by weight of a fragrance composition of a one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at least 20% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and ii) a silicone-in-water emulsion comprising at least one surfactant.

The invention is directed, in a second aspect, to a composition, wherein the composition is a hair care preparation, comprising: i) a fragrance composition; and ii) a silicone-in-water emulsion comprising at least one surfactant, wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of less than 2 μm . There is further provided a composition, wherein the composition is a

hair care preparation, comprising: i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 15% by weight of a fragrance composition of a one or more
5 perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at least 20% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and ii) a silicone-in-water emulsion comprising at least one surfactant.

The invention is directed, in a third aspect, to a method of cleansing hair,
10 which comprises applying to the hair a hair care preparation comprising: i) a fragrance composition; and ii) a silicone-in-water emulsion comprising at least one surfactant, wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of less than 2 μm . The invention is further directed to a method of cleansing hair, which comprises applying to the hair a hair care preparation comprising:
15 i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 15% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at least 20% by weight of a
20 fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and ii) a silicone-in-water emulsion comprising at least one surfactant.

In certain aspects, the aforementioned fragrance compositions may comprise a) at least 10.0% by weight of a fragrance composition of one or more
25 perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0;

b) at least 20% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at least 30% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C.

5 **DETAILED DESCRIPTION OF THE INVENTION**

In one aspect of the invention, there is provided a composition comprising i) a fragrance composition; and ii) a silicone-in-water emulsion comprising at least one surfactant, wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of less than 2 μm . There is further provided

10 a composition comprising: i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 15% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at

15 least 20% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and ii) a silicone-in-water emulsion comprising at least one surfactant. There is further provided a composition comprising:

i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having

20 a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 20% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at least 30% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and ii) a silicone-in-water emulsion comprising at least one


25 surfactant.

Silicone-in-water emulsions

The silicone-in-water emulsion used in the present invention may be prepared by emulsion polymerisation methods well-known in the art, such as those
5 described in U.S. 5,998,537 and EP 0874017, incorporated herein by reference. In summary, this method comprises a) mixing materials comprising a composition containing at least one polysiloxane, at least one organosilicon material that reacts with the polysiloxane by a chain extension reaction, a metal containing catalyst for said chain extension reaction, at least one surfactant, and water to form a mixture, and b)
10 emulsifying the mixture. This method provides a route to silicone-in-water emulsions having a wide range of physical characteristics, in particular emulsions wherein the dispersed silicone has a high viscosity and low droplet size.

Chain extension reactions with polysiloxanes are known in the art and can involve, for instance, the hydrosilylation reaction in which an Si-H reacts with an
15 aliphatically unsaturated group in the presence of a platinum or rhodium-containing catalyst forming polysiloxanes having some Si-(C)_p-Si links (wherein p = 1-6), which polysiloxanes may also be referred to as polysiloxane polysilalkylene copolymers. Alternatively, the chain extension reaction can involve the reaction of an Si-OH group (e.g., a hydroxy-terminated polysiloxane) with an alkoxy group (e.g., alkoxysilanes,
20 silicates, or alkoxysiloxanes) in the presence of a metal containing catalyst forming polysiloxane materials.

The polysiloxanes used in the chain extension reactions described above generally comprise a substantially linear polymer of the structure (I):



In this structure, each R independently represents a hydrocarbon group having up to 20 carbon atoms, preferably 1 to 6 carbon atoms, such as an alkyl group (e.g., methyl, ethyl, propyl or butyl), an aryl group (e.g., phenyl), or the group required for the chain extension reaction described above (“reactive group”, e.g., silicon-bonded hydrogen atoms, aliphatically unsaturated groups such as vinyl, allyl or hexenyl, hydroxy, alkoxy such as methoxy, ethoxy or propoxy, alkoxy-alkoxy, acetoxy, amino and the like), provided that on average there is from one to two reactive groups (inclusive) per polymer, and n is a positive integer greater than one. Preferably, a majority, more preferably >90%, and most preferably >98% of the reactive groups are substituted on the terminal silicone atom in the siloxane. Preferably, n is an integer which results in polysiloxanes with viscosities between about 1 and about 1 million mm^2s^{-1} , preferably from 1000 to 100,000 mm^2s^{-1} .

The polysiloxane (I) can have a small amount of branching (e.g., less than 2 mole % of the siloxane units), but preferably, wherein the polymers are substantially linear, more preferably completely linear. Moreover, the R groups can be substituted with, for example, nitrogen containing groups (e.g., amino groups), epoxy groups, sulfur-containing groups, silicon-containing groups, oxygen-containing groups and the like. Preferably, however, at least 80% of the R groups are alkyl and, more preferably, the alkyl groups are methyl groups.

The organosilicon material that reacts with the polysiloxane by a chain extension reaction can be either a second polysiloxane or a material which acts as a

chain extension agent. If the organosilicon material is a polysiloxane, then it too will generally have the structure described above (I). In such a situation, one polysiloxane in the reaction will comprise one reactive group and the second polysiloxane will comprise a second reactive group that reacts with the first.

5 If the organosilicon material comprises a chain extension agent, it can be a material such as a silane, a siloxane (e.g., disiloxane or trisiloxane) or a silazane. For example, a composition comprising a polysiloxane according to the above structure (I) which has at least one Si-OH group can be chain extended by using an alkoxysilane (e.g., a dialkoxysilane or trialkoxysilane) in the presence of a tin or titanium containing
10 catalyst.

The metal containing catalysts used in the above described chain extension reactions are often specific to the particular reaction. Such catalysts, however, are known in the art. Generally, they are materials containing metals such as platinum, rhodium, tin, titanium, copper, lead, etc.

15 In a preferred chain-extension reaction, a polysiloxane having at least one aliphatically unsaturated group, preferably an end-group, is reacted with an organosilicon material that is a siloxane or a polysiloxane having at least one Si-H group, preferably an end group, in the presence of a hydrosilylation catalyst. The polysiloxane having at least one aliphatically unsaturated group has the structure (I)
20 wherein R and n are as defined above and provided that on average between one and two (inclusive) R groups comprise an aliphatically unsaturated group per polymer. Representative aliphatically unsaturated groups include vinyl, allyl, hexenyl and cyclohexenyl or a group $R^2CH=CHR^3$, where R^2 represents a divalent aliphatic chain linked to the silicon atom and R^3 represents a hydrogen atom or an alkyl group. The
25 organosilicon material having at least one Si-H group preferably has the above structure

(I) wherein R and n are as defined above and provided that on average between one and two (inclusive) R groups comprise hydrogen atoms and n is 0 or a positive integer.

This material can be a polymer or a lower molecular weight material such as a siloxane (e.g. a disiloxane or a trisiloxane).

5 The polysiloxane having at least one aliphatically unsaturated group and the organosilicon material having at least one Si-H group react in the presence of a hydrosilylation catalyst. Such catalysts are known in the art and include, for example, platinum and rhodium-containing materials. These catalysts may take any of the known forms, such as platinum or rhodium deposited on carriers such as silica gel or
10 powdered charcoal, or other appropriate compounds such as platonic chloride, salts of platinum and chloroplatinic acids. A preferred material is chloroplatinic acid either as the commonly obtainable hexahydrate or the anhydrous form because of its easy dispersibility in organosilicon systems and its non-effect on colour of the mixture. Platinum or rhodium complexes may also be used, for example those prepared from
15 chloroplatinic acid hexahydrate and divinyltetramethyldisiloxane. Generally, these catalysts are used in amounts of between about 0.0001 and 10 wt. % based on the weight of the composition (I).

In a second preferred chain extension reaction, a polysiloxane having at least one Si-OH group, preferably an end group, is reacted with an organosilicon
20 material having at least one alkoxy group, preferably a siloxane having at least one Si-OR group, or an alkoxysilane having at least two alkoxy groups in the presence of a metal containing catalyst. In this case, the polysiloxane having at least one SiOH group has the structure (I) wherein R and n are as defined above and on average between one and two (inclusive) R groups comprise a hydroxyl group (OH). The organosilicon
25 material having at least one alkoxy group can have the structure (I) wherein R and n are

as defined above and on average between one and two (inclusive) R groups comprise alkoxy groups, e.g., of the structure (OR) in which R is as defined above and n is 0 or a positive integer. Alternatively, the organosilicon material can be a silane of the structure $R_mSi(OR)_{4-m}$, wherein R is as defined above and m is 0 to 2. Other materials
5 containing the alkoxy group (e.g., alkoxy- alkoxy) may also be used.

A variety of metal catalysts for the reaction of an Si-OH group with an Si-OR group are known in the art and may be employed including, for example, organic metal compounds such as organotin salts, titanates, or titanium chelates or complexes. Examples include stannous octoate, dibutyltin dilaurate, dibutyltin
10 diacetate, dimethyltin dineodecanoate, dibutyltin dimethoxide, isobutyl tin triceroate, dimethyltin dibutyrate, dimethyltin dineodecanoate, triethyltin tartrate, tin oleate, tin naphthenate, tin butyrate, tin acetate, tin benzoate, tin sebacate, tin succinate, tetrabutyl titanate, tetraisopropyl titante, tetraphenyl titante, tetraoctadecyl titanate, titanium naphthanate, ethyltriethanolamine titante, titanium diiso-propyl diethyl acetoacetate,
15 titanium diisopropoxy diacetyl acetate, and titanium tetra alkoxides where the alkoxide is butoxy or propoxy. Generally, these catalysts are used in amounts of between about 0.001 and 10 wt. % based on the weight of the composition (I).

Any composition containing at least one polysiloxane, at least one organosilicon material which reacts with said polysiloxane by a chain extension
20 reaction, and a metal containing catalyst for said chain extension reaction can be used for the chain extension reaction.

The dispersed silicone in the emulsion used in the present invention has a viscosity of preferably 100 million mm^2s^{-1} or more, more preferably 150 million mm^2s^{-1} or more, and most preferably 170 million mm^2s^{-1} or more, and a particle size of
25 preferably 2 μm or less, more preferably 1 μm or less, and most preferably 0.5 μm or

less. (Viscosities are measured at 25°C and atmospheric pressure.) It is also a preferred option that the particle size is small enough to cause the emulsion to be a microemulsion.

The emulsion preferably comprises at least 50% wt. silicone, more preferably at least 60 wt. %, even more preferably 75 wt. %. In addition to the polymerised silicone, the emulsion may also contain up to 2.5% by weight, based on the total weight of silicone, of a volatile silicone, which is mainly selected from cyclic siloxanes, preferably dimethyl cyclo polysiloxanes, and short chain polysiloxanes, preferably polydimethyl siloxanes with a chain length of no more than 10 siloxane units.

The preferred silicone-in-water emulsions of the invention are non-ionic and the silicone is a linear polysiloxane polysilalkylene copolymer, wherein the monovalent silicone substituents are substantially all C₁₋₆ hydrocarbon groups and the copolymer has a viscosity of 150 million mm²s⁻¹ or more and a particle size of 1 µm or less. In a more preferred embodiment, the silicone-in-water emulsion is a non-ionic emulsion comprising about 60 % by weight of a linear silicone copolymer formed by the hydrosilylation of a Si-H end-blocked polydimethyl siloxane and a vinyl-end-blocked polydimethyl siloxane, wherein the copolymer has a viscosity of about 170 mm²s⁻¹ and a particle size of about 0.5 µm, and about 5 % by weight of non-ionic surfactants.

Surfactants

The mixture used to form the emulsion also contains at least one surfactant. This can be a non-ionic surfactant, a cationic surfactant, an anionic surfactant, alkylpolysaccharides, amphoteric surfactants and the like.

Examples of non-ionic surfactants include polyoxyalkylene alkyl ethers, polyoxyalkylene sorbitan alkyl esters, polyoxyalkylene alkyl esters, and polyoxyalkylene alkylphenol ethers, polyethylene glycols, polypropylene glycols, and diethylene glycols. Particular examples include BRIJ35 and BRIJ30 (ICI Chemicals).

- 5 Examples of cationic surfactants include quaternary ammonium hydroxides such as tetramethylammonium hydroxide, octyltrimethylammonium hydroxide, dodecyl-trimethyl ammonium hydroxide, hexadecyltrimethyl ammonium hydroxide, octyldimethylbenzylammonium hydroxide, decyldimethylbenzyl ammonium hydroxide, didodecyldimethyl ammonium hydroxide, dioctadecyl
- 10 dimethylammonium hydroxide, tallow trimethylammonium hydroxide and cocotrimethylammonium hydroxide as well as corresponding salts of these materials, fatty acid amines and amides and their derivatives and the salts of the fatty acid amines and amides including aliphatic fatty amines and their derivatives, homologs of aromatic amines having fatty chains, fatty amides derived from aliphatic diamines, fatty amides
- 15 derived from disubstituted amines, derivatives of ethylene diamine, amide derivatives of amino alcohols, amine salts of long chain fatty acids, quaternary ammonium bases derived from fatty amides of disubstituted diamines quaternary ammonium bases of benzimidazolines, basic compounds of pyridinium and its derivatives, sulfonium compounds, quaternary ammonium compounds of betaine, urethanes of ethylene
- 20 diamine, polyethylene diamines and polypropanolpolyethanol amines.

- Examples of suitable anionic surfactants include alkyl sulfates such as lauryl sulfate, polymers such as acrylates/C₁₀₋₃₀ alkyl acrylate crosspolymer alkylbenzenesulfonic acids and salts such as hexylbenzenesulfonic acid, octylbenzenesulfonic acid, decylbenzenesulfonic acid, dodecylbenzenesulfonic acid,
- 25 cetylbenzenesulfonic acid and myristylbenzenesulfonic acid; the sulfate esters of

monoalkyl polyoxyethylene ethers; alkyl naphthylsulfonic acid; alkali metal sulfonates, sulfonated glyceryl esters of fatty acids such as sulfonated monoglycerides of coconut oil acids, salts of sulfonated monovalent alcohol esters, amides of amino sulfonic acids, sulfonated products of fatty acid nitriles, sulfonated aromatic hydrocarbons, condensation products of naphthalene sulfonic acids with formaldehyde, sodium octahydroanthracene sulfonate, alkali metal alkyl sulfates, ester sulfates, and alkaryl sulfonates.

Examples of suitable alkyl polysaccharides include, for example, materials of the structure $R^1-O-(R^2O)_x-(G)_y$ wherein R^1 represents a linear or branched alkyl group, a linear or branched alkenyl group or an alkylphenyl group, R^2 represent an alkylene group, G represents a reduced sugar, x denotes 0 or a positive integer and y denotes a positive integer as described, for example, in US Patent 5,035,832, incorporated herein by reference.

Examples of suitable amphoteric surfactants include cocamidopropyl betaine and cocamidopropyl hydroxysulfate.

The above surfactants may be used individually or in combination.

Fragrance compositions

The fragrances of the present invention comprise a) at least 10.0% by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 15% by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more, and c) at least 20% by weight of the fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C. Examples of these three classes of perfume ingredients are

illustrated in Tables 1-3. The specific ingredients in these Tables are illustrative only and other materials familiar to those skilled in the art that fall within the guidelines above can also be incorporated into the fragrance compositions of the present invention.

5 The fragrance compositions of the invention preferably comprise at least 20.0% by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; at least 15% by weight of the fragrance composition of a one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and at least 30% by weight of
10 the fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C. The fragrances compositions of the invention more preferably comprise: a) 30.0 to 40.0 % by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) 20.0 to 25.0 % by weight of the fragrance composition of one or more perfume
15 ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) 40.0 to 45.0 % by weight of the fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C.

 The fragrance compositions of the invention include as examples, but are not limited to fragrance 890656 and fragrance 862883. Fragrance 890656
20 comprises a) 31.03 % by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) 20.17 % by weight of the fragrance composition of a one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) 44.91 % by weight of the fragrance composition of one or more perfume ingredients have a boiling
25 point of greater than 250 °C. Fragrance 890656 comprises 12.79 % Di propylene

glycol; 12.00 % Linalyl acetate; 9.00 % Hexyl cinnamic aldehyde; 7.50 % Tonalide;
 7.38 % Benzyl salicylate; 6.05% Phenyl ethyl alcohol; 4.89 % Linalool; 4.50 %
 Vertenex; 10.01 % apple base; 4.93 % ozonic base; 9.84 % woody base; 10.61 % floral
 base; and .50 % oils or resins. Apple base, ozonic base, woody base, and floral base are
 5 fragrances comprising one or more perfume ingredients that have the combined
 indicated characteristic. Fragrance 890656 has the fragrance description of citrus,
 green, lemon, melon, apple, woody, jasmin, herbal, peach, muguet, and musk.

Fragrance 862883 comprises a) 34.08 % by weight of the fragrance
 composition of one or more perfume ingredients having a boiling point of 250 °C or
 10 less and ClogP of less than 3.0; b) 23.10 % by weight of the fragrance composition of
 a one or more perfume ingredients having a boiling point of 250 °C or less and ClogP
 of 3.0 or more; and c) 42.46 % by weight of the fragrance composition of one or more
 perfume ingredients have a boiling point of greater than 250 °C. Fragrance 862883
 comprises 18.98 % Di propylene glycol; 7.35 Verdox; 4.48 % Hedion; 4.47 %
 15 Linalool; 4.30 % Benzyl salicylate; 4.23 % Methyl hydrocinnamic aldehyde; 4.06 %
 Dihydro myrcenol; 4.25 % Citrus oil; 3.56 % Benzyl acetate; 3.27 % Hexyl cinnamic
 aldehyde; 2.04 % Benzyl Benzoate; 1.36 % Linalyl acetate; 18.12 % apple base; 5.07 %
 floral sandelwood base; 4.91 % fruit base; 5.77 % green base; and 3.78 % oils or resins.
 Apple base, floral sandelwood base, fruit base, and green base are fragrances
 20 comprising one or more perfume ingredients that have the combined indicated
 characteristic. Fragrance 862883 has the fragrance description of apple blossom, fruity,
 apple, floral, sandalwood, and musk.

The boiling points (BP) of many perfume ingredients, at standard 760
 mmHg are given in, e.g., "Perfume and Flavor Chemicals (Aroma Chemicals)," Steffen
 25 Arctander, published by the author, 1969, incorporated herein by reference. The

octanol/water partition coefficient of a fragrance ingredient is the ratio between its equilibrium concentrations in octanol and in water. The partition coefficients of the preferred perfume ingredients of the present invention may be more conveniently given in the form of their logarithm to the base 10, logP. The logP values of many perfume ingredients have been reported; for example, the Pomona92 database, available from Daylight Chemical Information Systems, Inc. (Daylight CIS), Irvine, Calif., contains many, along with citations to the original literature. However, the logP values are most conveniently calculated by the "CLOGP" program, also available from Daylight CIS. This program also lists experimental logP values when they are available in the Pomona database. The "calculated logP" (ClogP) is determined by the fragment approach of Hansch and Leo (cf., A. Leo, in Comprehensive Medicinal Chemistry, Vol. 4, C. Hansch, P. G. Sammens, J. B. Taylor and C. A. Ramsden, Eds., p. 295, Pergamon Press, 1990, incorporated herein by reference). The fragment approach is based on the chemical structure of each perfume ingredient, and takes into account the numbers and types of atoms, the atom connectivity, and chemical bonding. The ClogP values, which represent the octanol/water partition coefficient of a fragrance ingredient, are the most reliable and widely used estimates for this physicochemical property and are preferably used instead of the experimental logP values in the selection of perfume ingredients which are useful in the present invention.

TABLE 1. Perfume materials with boiling point less than or equal to 250 °C and CLogP less than 3.0

	<u>Name</u>	<u>BP</u>	<u>CLogP</u>
25	Allyl Caproate	185	2.772
	Amyl Acetate	142	2.258
	Amyl Propionate	161	2.657
	Anisic Aldehyde	248	1.779
	Anisole	154	2.061
30	Benzaldehyde	179	1.480
	Benzyl Acetate	215	1.960

	Benzyl Acetone	235	1.739
	Benzyl Alcohol	205	1.100
	Benzyl Formate	202	1.414
	Benzyl Iso Valerate	246	2.887
5	Benzyl Propionate	222	2.489
	Beta Gamma Hexenol	157	1.337
	Camphor Gum	208	2.117
	laevo-Carveol	227	2.265
	d-Carvone	231	2.010
10	laevo-Carvone	230	2.203
	Cinnamyl Formate	250	1.908
	cis-Jasmone	248	2.712
	cis-3-Hexenyl Acetate	169	2.243
	Cuminic alcohol	248	2.531
15	Cuminic aldehyde	236	2.780
	Cyclal C	180	2.301
	Dimethyl Benzyl Carbinol	215	1.891
	Dimethyl Benzyl Carbonyl Acetate	250	2.797
	Ethyl Acetate	77	0.730
20	Ethyl Aceto Acetate	181	0.333
	Ethyl Amyl Ketone	167	2.307
	Ethyl Benzoate	212	2.640
	Ethyl Butyrate	121	1.729
	Ethyl Hexyl Ketone	190	2.916
25	Ethyl-2-methyl butyrate	131	2.100
	Ethyl Methyl Pentanoate	143	2.700
	Ethyl Phenyl Acetate	229	2.489
	Eucalyptol	176	2.756
	Fenchyl Alcohol	200	2.579
30	Flor Acetate (tricyclo Decenyl Acetate)	175	2.357
	Frutene (tricyclo Decenyl Propionate)	200	2.260
	Geraniol	230	2.649
	Hexenol	159	1.397
	Hexenyl Acetate	168	2.343
35	Hexyl Acetate	172	2.787
	Hexyl Formate	155	2.381
	Hydratropic Alcohol	219	1.582
	Hydroxycitronellal	241	1.541
	Isoamyl Alcohol	132	1.222
40	Isomenthone	210	2.831
	Isopulegyl Acetate	239	2.100
	Isoquinoline	243	2.080
	Ligustral	177	2.301
	Linalool	198	2.429
45	Linalool Oxide	188	1.575
	Linalyl Formate	202	2.929
	Menthone	207	2.650
	Methyl Acetophenone	228	2.080
	Methyl Amyl Ketone	152	1.848
50	Methyl Anthranilate	237	2.024

	Methyl Benzoate	200	2.111
	Methyl Benzyl Acetate	213	2.300
	Methyl Eugenol	249	2.783
	Methyl Heptenone	174	1.703
5	Methyl Heptine Carbonate	217	2.528
	Methyl Heptyl Ketone	194	1.823
	Methyl Hexyl Ketone	173	2.377
	Methyl Phenyl Carbinyl Acetate	214	2.269
	Methyl Salicylate	223	1.960
10	Nerol	227	2.649
	Octalactone	230	2.203
	Octyl Alcohol (Octanol-2)	179	2.719
	para-Cresol	202	1.000
	para-Cresyl Methyl Ether	176	2.560
15	para-Methyl Acetophenone	228	2.080
	Phenoxy Ethanol	245	1.188
	Phenyl Acetaldehyde	195	1.780
	Phenyl Ethyl Acetate	232	2.129
	Phenyl Ethyl Alcohol	220	1.183
20	Phenyl Ethyl Dimethyl Carbinol	238	2.420
	Prenyl Acetate	155	1.684
	Propyl Butyrate	143	2.210
	Pulegone	224	2.350
	Rose Oxide	182	2.896
25	Safrole	234	1.870
	4-Terpinenol	212	2.749
	alpha-Terpineol	219	2.569
	Viridine	221	1.293

30

TABLE 2. Perfume materials with boiling point less than or equal to 250 °C and CLogP greater than or equal to 3.0

	Name	BP	CLogP
35	Zallo-Ocimene	192	4.362
	Allyl Heptoate	210	3.301
	Anethol	236	3.314
	Benzyl Butyrate	240	3.698
	Camphene	159	4.192
40	Carvacrol	238	3.401
	cis-3-Hexenyl Tiglate	101	3.700
	Citral (Neral)	228	3.120
	Citronellol	225	3.193
	Citronellyl Acetate	229	3.670
45	Citronellyl Isobutyrate	249	4.937
	Citronellyl Nitrile	225	3.094
	Citronellyl Propionate	242	4.628
	Cyclohexyl Ethyl Acetate	187	3.321
	Decyl Aldehyde	209	4.008
50	Delta Damascone	242	3.600

	Dihydro Myrcenol	208	3.030
	Dihydromyrcenyl Acetate	225	3.879
	Dimethyl Octanol	213	3.737
	Fenchyl Acetate	220	3.485
5	gamma Methyl Ionone	230	4.089
	gamma-Nonalactone	243	3.140
	Geranyl Acetate	245	3.715
	Geranyl Formate	216	3.269
	Geranyl Isobutyrate	245	4.393
10	Oeranyl Nitrile	222	3.139
	Hexenyl Isobutyrate	182	3.181
	Hexyl Neopentanoate	224	4.374
	Hexyl Tiglate	231	3.800
	alpha-Ionone	237	3.381
15	beta-Ionone	239	3.960
	gamma-Ionone	240	3.780
	alpha-Irone	250	3.820
	Isobornyl Acetate	227	3.485
	Isobutyl Benzoate	242	3.028
20	Isononyl Acetate	200	3.984
	Isononyl Alcohol	194	3.078
	Isomenthol	219	3.030
	para-Isopropyl Phenylacetaldehyde	243	3.211
	Isopulegol	212	3.330
25	Lauric Aldehyde (Dodecanal)	249	5.066
	d-Limonene	177	4.232
	Linalyl Acetate	220	3.500
	Menthyl Acetate	227	3.210
	Methyl Chavicol	216	3.074
30	alpha-iso "gamma" Methyl Ionone	230	4.209
	Methyl Nonyl Acetaldehyde	232	4.846
	Methyl Octyl Acetaldehyde	228	4.317
	Myrcene	167	4.272
	Neral	228	3.320
35	Neryl Acetate	231	3.555
	Nonyl Acetate	212	4.374
	Nonyl Aldehyde	212	3.479
	Octyl Aldehyde	223	3.845
	Orange Terpenes (d-Limonene)	177	4.232
40	para-Cymene	179	4.068
	Phenyl Ethyl Isobutyrate	250	3.000
	alpha-Pinene	157	4.122
	beta-Pinene	166	4.182
	alpha-Terpinene	176	4.412
45	gamma-Terpinene	183	4.232
	Terpinolene	184	4.232
	Terpinyl acetate	220	3.475
	Tetrahydro Linalool	191	3.517
	Tetrahydro Myrcenol	208	3.517
50	Undecenal	223	4.053

Veratrol	206	3.140
Verdox	221	4.059
Vertenex	232	4.060

5

TABLE 3. Perfume materials with boiling point greater than 250 °C

	Name	BP	CLogP
	Allyl Cyclohexane Propionate	267	3.935
10	Ambrettolide	300	6.261
	Amyl Benzoate	262	3.417
	Amyl Cinnamate	310	3.771
	Amyl Cinnamic Aldehyde	285	4.324
	Amyl Cinnamic Aldehyde Dimethyl Acetal	300	4.033
15	iso-Amyl Salicylate	277	4.601
	Aurantiol	450	4.216
	Benzophenone	306	3.120
	Benzyl Salicylate	300	4.383
	Cadinene	275	7.346
20	Cedrol	291	4.530
	Cedryl Acetate	303	5.436
	Cinnamyl Cinnamate	370	5.480
	Coumarin	291	1.412
	Cyclohexyl Salicylate	304	5.265
25	Cyclamen Aldehyde	270	3.680
	Dihydro Isojasmonate	300	3.009
	Diphenyl Methane	262	4.059
	Ethylene Brassylate	332	4.554
	Ethyl Methyl Phenyl Glycidate	260	3.165
30	Ethyl Undecylenate	264	4.888
	iso-Eugenol	266	2.547
	Exaltolide	280	5.346
	Galaxolide	260	5.482
	Oeranyl Anthranilate	312	4.216
35	Hexadecanolide	294	6.805
	Hexenyl Salicylate	271	4.716
	Hexyl Cinnamic Aldehyde	305	5.473
	Hexyl Salicylate	290	5.260
	Linalyl Benzoate	263	5.233
40	2-Methoxy Naphthalene	275	3.235
	Methyl Cinnamate	263	2.620
	Methyl Dihydrojasmonate	300	2.275
	beta-Methyl Naphthyl ketone	300	2.275
	Musk Indanone	>250	5.458
45	Musk Ketone	137 (MP)	3.014
	Musk Tibetine	136 (MP)	3.831
	Myristicin	276	3.200
	delta-Nonalactone	280	2.760
	Oxahexadecanolide-10	300	4.336
50	Oxahexadecanolide-11	35 (MP)	4.336

	Patchouli Alcohol	285	4.530
	Phantolide	288	5.977
	Phenyl Ethyl Benzoate	300	4.058
	Phenylethylphenylacetate	325	3.767
5	alpha-Santalol	301	3.800
	Thibetolide	280	6.246
	delta-Undecalactone	290	3.830
	gamma-Undecalactone	297	4.140
	Vanillin	285	1.580
10	Vetiveryl Acetate	285	4.882
	Yara-Yara	274	3.235

Hair Care Preparations

15 The silicone-in-water emulsion, wherein the dispersed silicone has a viscosity of at least, and preferably more than 100 million mm^2s^{-1} , and a particle size of at most, preferably less than 2 μm , is mixed with a fragrance composition in a weight ratio of preferably from 1:1 to 10:1 of silicone:fragrance. It is preferred that this mixing takes place prior to incorporation in a hair care preparation, as it enables a

20 greater control and consistency of the distribution and partitioning of the silicone and the fragrance in the hair care preparation. Mixing may take place by methods well-known in the art. For example, low shear mixing may take place by methods well-known in the art, as for example, regular hand mixing using low shear bench scale overhead mixing equipment, as for example a Heidolf RZR 50 stirrer with variable

25 speed range between 45-2000 RPM, or on a larger scale in a groin kettle or via large scale overhead mechanical drum mixing.

 The mixture is then incorporated in a hair care preparation in an amount which provides at least 1% silicone by weight of the hair care preparation, for example 1 to 10% by weight, or for example 2 to 6% wt. Hair care preparations, including

30 shampoos, conditioners and conditioning shampoos are well known in the art, and typically comprise a washing base containing surfactants, and other agents for

improving the cosmetic properties of the preparation. The washing base typically comprises a cosmetically acceptable aqueous medium, which may be solely water, or water with a solvent (for example, a lower alcohol or alkylene glycol). The surfactants may be anionic, non-ionic, cationic, or amphoteric. Other additives which may be

5 included in the preparation include pH adjusters (for example, amines), viscosity regulators, electrolytes or thickeners, pearlising or opacifying agents, foam synergists, and other agents for improving the properties of the preparation, for example anionic, non-ionic and cationic polymers, proteins, fatty acids and vitamins. The hair care preparation will typically be in the form of a liquid, a thickened liquid, a lotion or a gel.

10 The invention is directed to a composition, wherein the composition is a hair care preparation, comprising: i) a fragrance composition; and ii) a silicone-in-water emulsion comprising at least one surfactant, wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of less than 2 μm . The invention is further directed to a composition, wherein the composition is a hair care

15 preparation, comprising: i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 15% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at

20 least 20% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and ii) a silicone-in-water emulsion comprising at least one surfactant. The invention is further directed to a composition, wherein the composition is a hair care preparation, comprising: i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by

25 weight of a fragrance composition of one or more perfume ingredients having a boiling

point of 250 °C or less and ClogP of less than 3.0; b) at least 20% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at least 30% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than
5 250 °C; and ii) a silicone-in-water emulsion comprising at least one surfactant. In one embodiment, the silicone:fragrance composition weight ratio is from 1:1 to 10:1. In a further embodiment, the hair care preparation is a shampoo, a conditioner, or a conditioning shampoo.

The use of the above defined silicone-in-water emulsion in hair care
10 preparations according to the present invention can provide hair care preparations which have improved fragrance deposition on hair, measured as longer lasting fragrance release from the hair compared to conventional preparations. The improved fragrance deposition occurs without a loss of favorable sensory and aesthetic perception for the user normally associated with silicone deposition on hair, which includes ease of
15 combing, luster, shine and general conditioning.

It is particularly surprising that the combination of such high viscosity of the emulsified silicones with such low particle size results in the greater deposition of the fragrance or a longer lasting release of the fragrance from the hair, without negatively affecting the benefits of deposited silicones.

20 The invention is directed to a method of cleansing hair, which comprises applying to the hair a hair care preparation comprising: i) a fragrance composition; and ii) a silicone-in-water emulsion comprising at least one surfactant, wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of less than 2 μm .

The invention is also directed to a method of cleansing hair, which comprises applying to the hair a hair care preparation comprising: i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 15% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at least 20% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and ii) a silicone-in-water emulsion comprising at least one surfactant.

10 The invention is also directed to a method of cleansing hair, which comprises applying to the hair a hair care preparation comprising: i) a fragrance composition, wherein the fragrance composition comprises a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0; b) at least 20% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and c) at least 30% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and ii) a silicone-in-water emulsion comprising at least one surfactant.

In a preferred embodiment, the silicone:fragrance composition weight ratio is from 1:1 to 10:1. In a further preferred embodiment, the hair care preparation is a shampoo, a conditioner, or a conditioning shampoo.

The compositions of the invention may additionally be used in other cosmetic applications, in particular skin care applications, providing a similar benefit. Examples of suitable skin care applications include lotions, gels (including shower gels), jellies, pastes, facial applications, moisturizers, face masks, night creams, day

creams, sun milk, massage creams, make-up removal lotions, anti-aging cream, and anti-wrinkle cream.

The following Examples are provided for a further illustration of the invention, but are not intended to be limiting thereof. Unless otherwise indicated, all parts and percentages are by weight and all viscosities are dynamic viscosities measured at 25 °C.

Examples

10 Example 1

A silicone-in-water emulsion, SEM1, was made by mixing 58.5 parts dimethylvinyl-terminated polydimethylsiloxane having a viscosity of $55,000 \text{ mm}^2\text{s}^{-1}$ with 1.17 parts of dimethylhydrogen-terminated polydimethylsiloxane having a viscosity of $10 \text{ mm}^2\text{s}^{-1}$. To this mixture was added 2.05 parts of polyoxyethylene (3) lauryl ether and enough water to cause phase inversion. 2.8 parts of polyoxyethylene (23) lauryl ether were then added under high shear. Finally, water was added to a total of 35.5 parts water, in which the water was added in stages with mixing after each addition, followed by the addition of 0.012 parts of a platinum catalyst and 0.5 parts of Glydant Plus preservative. The resulting emulsion was a non-ionic emulsion containing about 60% by weight of a linear silicone polymer formed from the hydrosilylation of a Si-H end-blocked polydimethyl siloxane and a vinyl-end-blocked polydimethyl siloxane, in which the polymer has a viscosity of about 170 million mm^2s^{-1} and an average particle size of $0.5 \text{ }\mu\text{m}$. The silicone-in-water emulsion formed, SEM1, was mixed with fragrances and tested as described in the following Examples.

25

Example 2

Fragrance 862883 was mixed with the silicone-in-water emulsion, SEM1, in a 1:4 ratio by weight. The fragrance/silicone mixture was added at a concentration of 4% by weight to a shampoo base T-058.

5 Shampoo base T-058 is formed by mixing 0.30 % Methocel E4M (hydroxypropyl methylcellulose; Dow Chemical Co.) in hot deionized water at 80 - 90 °C with an overhead mixer at medium speed until all of the particles are wetted down and a consistent dispersion is obtained. 0.05 % Sequestrene Na₄ (tetrasodium EDTA; Ciba Geigy) was mixed at 85 °C with deionized water, was cooled down, and added to
10 the hot mixture. The resulting solution was cooled to 30 °C and mixing was continued for approximately 20 minutes. The mixture was reheated to 60 °C. 18.00 % Standapol T (TEA lauryl sulfate; Cognis/Henkel), 8.00 % Standapol A (ammonium lauryl sulfate; Cognis/Henkel), 4.00 % Monamid 150-LMWC (lauramide DEA; Uniqema), and 0.30 % Palmitic acid (Ruger) were added while mixing at low/medium speed using an
15 overhead mixer. 0.15 % Gydant (DMDM hydantoin; Lonza), approximately 0.3 % sodium chloride (to adjust viscosity), and approximately 0.5 % citric acid (to adjust pH to 5.5-6.0) was added while mixing at low/medium speed using an overhead mixer. The mixture was mixed at low speed until room temperature was reached to form T-058.

20 As a control, fragrance alone was added at a concentration of 0.8% by weight to the same shampoo base T-058. The fragrance/silicone mixture and the control each were added to half a head of two subjects. The hair was shampooed and the fragrance was evaluated by a panel of five perfume and odor evaluators at the stages of neat products, hair during lathering, hair after rinsing, hair after blow drying,
25 and hair 6 hours after drying. The evaluations were determined on a scale of 1-5 (1, no

fragrance, to 5, strong fragrance smell) for each subject. The evaluations for the two subjects were averaged and the evaluation results are summarized in Table 4.

5 **TABLE 4.** Effect of silicone on fragrance performance of hair care preparation.

Stage	4% fragrance/silicone mixture in shampoo base T-058	0.8 % fragrance mixture in shampoo base T-058
Neat	4.00	4.25
Lathering	3.25	2.75
Rinse	2.75	1.50
Blow-dry	2.50	1.75
6 hours after blow-dry	2.00	1.50

The results indicate that silicones have a significant effect on residual fragrance perception at the stages of lathering, rinse, blow-dry, and 6 hours after blow-dry.

10

Example 3

Fragrance 862883 was mixed with the silicone-in-water emulsion, SEM1, in a 1:4 ratio by weight. The fragrance/silicone mixture was added at a concentration of 4% by weight to a shampoo base T-058 (see Example 2). As a control, fragrance alone was added at a concentration of 0.8% by weight to the same shampoo base T-058. The fragrance/silicone mixture and the control were added to 6 swatches of hair each. The 12 hair swatches were shampooed and the fragrance was

evaluated by a panel of five perfume and odor evaluators at the stages of hair after rinsing, hair after blow drying, and hair 6 hours after drying. The evaluations were determined on a scale of 1-5 (1, no fragrance, to 5, strong fragrance smell) for each swatch. The evaluations by each evaluator and for all the swatches were averaged, and

5 the evaluation results are indicated in Table 5.

TABLE 5. Effect of silicone on fragrance performance of hair care preparation.

Stage	4% fragrance/silicone mixture in shampoo base T-058	0.8 % fragrance mixture in shampoo base T-058
Rinse	3.60	3.26
Blow-dry	3.02	2.75
6 hours after blow-dry	1.93	2.13

The results indicate that silicones have a positive effect on residual

10 fragrance perception at the stages of after rinse and after blow-dry.

Example 4

Fragrance 890656 was mixed with the silicone-in-water emulsion, SEM1, in a 1:8 ratio by weight. The fragrance/silicone mixture was added at a

15 concentration of 3.2% by weight to a conditioner base T-114.

Conditioner base T-114 is formed by heating deionized water to 70 °C and slowing adding 0.25 % methyl paraben (TRI-K) while mixing at medium speed until completely solubilized. The resulting composition is held at 70 °C. 1.50 % propylene glycol and 1.00 % Natrosol 250 HR (hydroxyethylcellulose; Hercules) are

- premixed into a slurry and added to the initial mixture. The resulting mixture is mixed at 70 °C until completely clear and hydrated. 1.00 % Ammonyx 4002 (stearalkonium chloride; Stephan) is slowly added to the mixture. 0.25 % Lipoquat R (ricinoleamidopropyl ethyldimonium ethosulfate; Lipo Chemicals, Inc.), 0.50 %
- 5 Lipopeg 6000 DS (PEG-150 distearate; Lipo Chemicals, Inc.), 1.00 % Lipowax D (cetearyl alcohol and cetareth-20; Lipo Chemicals, Inc.), and 0.10 % propyl paraben (TRI-K) were pre-heated until melted and clear and then added to the mixture while mixing on a homomixer at medium speed for 1 minute to form conditioner base T-114.

- As a control, fragrance alone was added at a concentration of 0.4% by
- 10 weight to the same conditioner base T-114. The fragrance/silicone mixture and the control were added to 6 swatches of hair each. The 12 hair swatches were conditioned and the fragrance was evaluated by a panel of five perfume and odor evaluators at the stages of hair after rinsing, hair after blow drying, and hair 6 hours after drying. The evaluations were determined on a scale of 1-5 (1, no fragrance, to 5, strong fragrance
- 15 smell) for each swatch. The evaluations by each evaluator and for all the swatches were averaged and the evaluation results are indicated in Table 6.

TABLE 6. Effect of silicone on fragrance performance of hair care preparation.

Stage	3.2% fragrance/silicone mixture in conditioner base T-114	0.4 % fragrance mixture in conditioner base T-114
Rinse	3.23	2.83
Blow-dry	2.68	2.42
6 hours after blow-dry	2.03	2.00

The results indicate that silicones have a positive effect on residual fragrance perception at the stages of after rinse and after blow-dry.

Example 5

5 Fragrance 862883 was mixed with the silicone-in-water emulsion, SEM2. SEM2 was prepared in a similar manner as SEM1 described in Example 1, except that the non-ionic surfactants were replaced with 3.4 parts of Bioterge AS 40 (Stephan Company) and less dimethylhydrogen-terminated polydimethylsiloxane was used, resulting in an anionic emulsion having a polymer with a viscosity of 300 million
10 mm^2s^{-1} and an average particle size of 1.1 μm . The emulsion and the fragrance were mixed in a 4:1 ratio by weight. The SEM2-based fragrance/silicone mixture was added at a concentration of 4% by weight to a shampoo base T-058 (see Example 2).

 Fragrance 862883 was mixed with the silicone-in-water emulsion, SEM8. SEM8 was prepared in a similar manner as SEM1 described in Example 1,
15 except that in addition, 4 parts of an alkylmethyl siloxane polymer of about 10 mm^2s^{-1} having a C_{30} alkyl substituent on each silicon atom, was added. The emulsion had an average particle size of 0.8 μm . The emulsion was mixed with fragrance in a 4:1 ratio by weight. The SEM8-based fragrance/silicone mixture was added at a concentration of 4% by weight to a shampoo base T-058.

20 As a control, fragrance alone was added at a concentration of 0.8% by weight to the same shampoo base T-058. The fragrance/silicone mixtures and the control were added to 3 swatches of hair each. The 9 hair swatches were shampooed and the fragrance was evaluated by a panel of six perfume and odor evaluators at the stages of hair after rinsing, hair after blow drying, and hair 6 hours after drying. The
25 evaluations were determined on a scale of 1-5 (1, no fragrance, to 5, strong fragrance

smell) for each swatch. The evaluations by each evaluator and for all the swatches were averaged and the evaluation results are indicated in Table 7.

TABLE 7. Effect of silicone on fragrance performance of hair care preparation.

Stage	4% SEM2-based fragrance/silicone mixture in shampoo base T-058	4% SEM8-based fragrance/silicone mixture in shampoo base T-058	0.4 % fragrance mixture in shampoo base T- 058
Rinse	2.82	3.44	3.29
Blow-dry	2.00	2.71	2.74
6 hours after blow-dry	1.58	1.94	1.98

5

The results indicate that the SEM2 and SEM8-based mixtures do not have a consistent positive effect on residual fragrance perception.

Example 6

10 Fragrance 862883 was mixed with the silicone-in-water emulsion, SEM1, in a 1:4 ratio by weight. The SEM1-based fragrance/silicone mixture was added at a concentration of 4% by weight to a shampoo base T-058 (see Example 2).

 Fragrance 862883 was mixed with the silicone-in-water emulsion, SEM4, in a 1:4 ratio by weight. SEM4 was made in a similar way to SEM1 described
 15 in Example 1, however the resulting emulsion has a viscosity of $138 \text{ million mm}^2 \text{ s}^{-1}$ and an average particle size of $0.35 \text{ }\mu\text{m}$. The SEM4-based fragrance/silicone mixture was added at a concentration of 4% by weight to a shampoo base T-058.

Fragrance 862883 was mixed with the silicone-in-water emulsion, SEM5, in a 1:4 ratio by weight. SEM5 was made in a similar fashion as SEM1 described in Example 1, but the resulting emulsion had a viscosity of 272 million mm^2s^{-1} and an average particle size of 0.36 μm . The SEM5-based fragrance/silicone mixture was added at a concentration of 4% by weight to a shampoo base T-058.

As a control, fragrance alone was added at a concentration of 0.8% by weight to the same shampoo base T-058. The fragrance/silicone mixtures and the control were added to 3 swatches of hair each. The 12 hair swatches were shampooed and the fragrance was evaluated by a panel of six perfume and odor evaluators at the stages of hair after rinsing, hair after blow drying, and hair 6 hours after drying. The evaluations were determined on a scale of 1-5 (1, no fragrance, to 5, strong fragrance smell) for each swatch. The evaluations by each evaluator and for all the swatches were averaged and the evaluation results are indicated in Table 8.

TABLE 8. Effect of silicone on fragrance performance of hair care preparation.

Stage	4% SEM1-based fragrance/silicone mixture in shampoo base T-058	4% SEM4-based fragrance/silicone mixture in shampoo base T-058	4% SEM5-based fragrance/silicone mixture in shampoo base T-058	0.8 % fragrance mixture in shampoo base T-058
Rinse	3.72	3.36	3.58	3.10
Blow-dry	3.43	2.97	3.07	2.92
6 hours after blow-dry	2.11	1.83	2.03	1.64

The results indicate that the SEM1, SEM4, and SEM5-based mixtures all give a positive effect on residual fragrance perception. Furthermore, SEM1-based mixture give a better effect than SEM4 or SEM5-based mixtures.

5

Example 7

Compositions of shampoo base T-058 alone or in combination with silicone-in-water emulsion SEM1 and/or fragrance 862883 were formulated according to the ingredients and amounts given in Table 9. The viscosity of the resulting compositions are shown in Table 9. Addition of silicone-in-water emulsion SEM1 to shampoo base T-058 reduced the viscosity of the shampoo base T-058 by about 15%. Addition of fragrance 862883 increased the viscosity of shampoo base T-058 over 2.5-fold. When added to shampoo base T-058, the combination of silicone-in-water emulsion SEM1 and fragrance 862883 exhibited a viscosity reduction of about 15%, relative to addition of fragrance 862883 alone.

15

TABLE 9. Effect of silicone on viscosity of shampoo-fragrance compositions

Composition	Viscosity (cps)
Shampoo base T-058	2020
Shampoo base T-058 + 3.2% silicone-in-water emulsion SEM1	1700
Shampoo base T-058+ 0.8% fragrance 862883	5450
Shampoo base T-058 + 3.2% silicone-in-water emulsion SEM1 + 4.0% fragrance 862883	4530

The present invention is not to be limited in scope by the specific embodiments described herein. Various modifications of the invention in addition to those described herein will become apparent to those skilled in the art from the foregoing description. Such modifications are intended to fall within the scope of the

5 appended claims.

All patents, applications, publications, test methods, literature, and other materials cited herein are hereby incorporated by reference.

WE CLAIM:

1. A composition comprising:
 - i) a fragrance composition; and
 - 5 ii) a silicone-in-water emulsion comprising at least one surfactant, wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of 2 μm or less.
- 10 2. The composition of claim 1, wherein the silicone-in-water emulsion is non-ionic and the silicone is a linear polysiloxane polysilalkylene copolymer, wherein the monovalent silicone substituents are substantially all C_{1-6} hydrocarbon groups and the copolymer has a viscosity of 150 million mm^2s^{-1} or more and a particle size of 1 μm or less.
- 15 3. The composition of claim 2, wherein the silicone-in-water emulsion is a non-ionic emulsion comprising about 60 % by weight of a linear silicone copolymer formed by the hydrosilylation of a Si-H end-blocked polydimethyl siloxane and a vinyl-end-blocked polydimethyl siloxane, wherein the copolymer has a viscosity of about 170 mm^2s^{-1} and a particle size of about 0.5 μm , and about 5 % by weight of non-ionic surfactants.
- 20 4. The composition of claim 1, wherein the fragrance composition comprises
 - a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0;
 - b) at least 15% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and
 - 25 c) at least 20% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C.
5. The composition of claim 4, wherein the fragrance composition comprises:
 - a) at least 20.0% by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0;

b) at least 15% by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and

5 c) at least 30% by weight of the fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C.

6. The composition of claim 5, wherein the fragrance composition comprises:

a) 30.0 to 40.0 % by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0;

10 b) 20.0 to 25.0 % by weight of the fragrance composition of a one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and

c) 40.0 to 45.0 % by weight of the fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C.

15 7. The composition of claim 1, wherein the silicone:fragrance composition weight ratio is from 1:1 to 10:1.

8. A composition comprising:

i) a fragrance composition, wherein the fragrance composition comprises

20 a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0,

b) at least 20% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or
25 more, and

c) at least 30% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and

ii) a silicone-in-water emulsion comprising at least one surfactant.

9. The composition of claim 8, wherein the dispersed silicone has a viscosity of
30 100 million mm²s⁻¹ or more and a particle size of 2 µm or less.

10. The composition of claim 9, wherein the silicone-in-water emulsion is non-ionic and the silicone is a linear polysiloxane polysilalkylene copolymer, wherein the monovalent silicone substituents are substantially all C₁₋₆ hydrocarbon groups and the copolymer has a viscosity of 150 million mm²s⁻¹ or more and a particle size of 1 μm or less.

11. The composition of claim 10, wherein the silicone-in-water emulsion is a non-ionic emulsion comprising about 60 % by weight of a linear silicone copolymer formed by the hydrosilylation of a Si-H end-blocked polydimethyl siloxane and a vinyl-end-blocked polydimethyl siloxane, wherein the copolymer has a viscosity of about 170 mm²s⁻¹ and a particle size of about 0.5 μm, and about 5 % by weight of non-ionic surfactants.

12. The composition of claim 8, wherein the fragrance composition comprises

- a) at least 20.0% by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0;
- b) at least 20% by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and
- c) at least 30% by weight of the fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C.

13. The composition of claim 12, wherein the fragrance composition comprises:

- a) 30.0 to 40.0 % by weight of the fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0;
- b) 20.0 to 25.0 % by weight of the fragrance composition of a one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and
- c) 40.0 to 45.0 % by weight of the fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C.

14. The composition of claim 8, wherein the silicone:fragrance composition weight ratio is from 1:1 to 10:1.

15. A composition, wherein the composition is a hair care preparation, comprising:

i) a fragrance composition; and

ii) a silicone-in-water emulsion comprising at least one surfactant,

5 wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of less than 2 μm .

16. The hair care preparation of claim 15, wherein the silicone:fragrance composition weight ratio is from 1:1 to 10:1.

17. The hair care preparation of claim 15, wherein the hair care preparation is a
10 shampoo, a conditioner, or a conditioning shampoo.

18. A composition, wherein the composition is a hair care preparation, comprising:

i) a fragrance composition, wherein the fragrance composition
comprises

15 a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0;

b) at least 20% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or
20 more; and

c) at least 30% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and

ii) a silicone-in-water emulsion comprising at least one surfactant.

19. The hair care preparation of claim 18, wherein the silicone:fragrance
25 composition weight ratio is from 1:1 to 10:1.

20. The hair care preparation of claim 18, wherein the hair care preparation is a shampoo, a conditioner, or a conditioning shampoo.

21. A method of cleansing hair, which comprises applying to the hair a hair care preparation comprising:

30 i) a fragrance composition; and

ii) a silicone-in-water emulsion comprising at least one surfactant, wherein the dispersed silicone has a viscosity of 100 million mm^2s^{-1} or more and a particle size of less than 2 μm .

22. The method of claim 21, wherein the silicone:fragrance composition weight
5 ratio is from 1:1 to 10:1.

23. The method of claim 21, wherein the hair care preparation is a shampoo, a conditioner, or a conditioning shampoo.

24. A method of cleansing hair, which comprises applying to the hair a hair care preparation comprising:

10 i) a fragrance composition, wherein the fragrance composition comprises

a) at least 10.0% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of less than 3.0;

15 b) at least 20% by weight of a fragrance composition of one or more perfume ingredients having a boiling point of 250 °C or less and ClogP of 3.0 or more; and

c) at least 30% by weight of a fragrance composition of one or more perfume ingredients have a boiling point of greater than 250 °C; and

20 ii) a silicone-in-water emulsion comprising at least one surfactant.

25. The method of claim 24, wherein the silicone:fragrance composition weight ratio is from 1:1 to 10:1.

26. The method of claim 24, wherein the hair care preparation is a shampoo, a conditioner, or a conditioning shampoo.